



SOLSTICE® LIQUID BLOWING AGENT

High Performance Refrigerator Insulation

A Near Drop-In Replacement, Energy-Efficient Blowing Agent

Where can you reduce weight?

Honeywell Solstice® Liquid Blowing Agent (LBA) is the latest advance in blowing agent technology. It is a low global warming potential (GWP), non-flammable, energy-efficient blowing agent for refrigerator and freezer insulation applications, and does not require platform design changes or process configuration modifications.

Performance

- Up to 10-12% better than hydrocarbon; 2% better than HFC-245fa. We expect even more as formulations are fine-tuned.
- Better energy efficiency performance at low temperatures.

Cost Effectiveness

Honeywell Solstice LBA cost-effectively delivers the lambda improvement to current, commercial PUR insulation, allowing OEMs to meet ever-increasing energy standards without the use of additional equipment such as vacuum insulated panels or variable speed compressors.

- A near drop-in replacement for liquid HCFC, HFC, hydrocarbons and other non-fluorocarbon blowing agents
- Does not require expensive hydrocarbon storage and handling or risk mitigation equipment

Value in Use

A recent refrigerator trial, comparing HFC-245fa with Solstice LBA, was performed in an existing operation, utilizing existing equipment/tooling, with no modifications to the foaming process.

- Minimum fill weights (which is a measure of flow characteristics) were nearly identical
- Cabinets and doors were overpacked such that the finished foam product density was in excess of 2 pounds/ft³
- Demold times for Solstice LBA PUR were equal to/improved over HFC-245fa PUR

Environmental Impact

Honeywell Solstice LBA is a promising replacement for foam insulation blowing agents currently in use, with the potential to make significant contributions to reductions in global warming. When substituted for HCFC-141b, HFC-245fa and HFC-365mfc, the use of Solstice LBA can yield substantial improvements in the environmental impact of foam blowing agents right away. With a GWP of 1, its widespread adoption could save about 60 million metric tons per year of

Solstice Liquid Blowing Agent Outperforms the Competition

	HFC 141b	Hydro Carbons	HFC 245fa	Solstice LBA
Performance				
Energy Efficiency	●	●	●	●
Cost				
Adoption Cost/Ease	●	●	●	●
Cost per Unit	●	●	●	●
Environment				
Global Warming Impact	●	●	●	●
Ozone Depletion Impact	●	●	●	●
Volatile Organics	●	●	●	●
Safety				
Flammability	●	●	●	●
Toxicity	●	●	●	●

Environmental and Safety Properties

	Solstice LBA	HCFC-141b
Atmospheric Life	26 days	10.8 years
ODP	~0*	0.11
GWP100	1	725
Flammable	No	No
Exposure Limit (OEL)	800ppm	500ppm

*No impact on ozone layer depletion and is commonly referred to as zero (Wuebbles, Private communication)

CO₂ equivalent, comparable to eliminating carbon dioxide emissions from more than 11.8 million cars every year. (Source: GHG Equivalencies Calculator: <http://www.epa.gov/cleanenergy/energyresourcescalculator.html>)

Safety


Solstice LBA is a non-flammable liquid by ASTM E-681, exhibits no flashpoint or vapor flame limits, and has no limitation on hazards classification. Solstice LBA has a very low Maximum Incremental Reactivity (MIR) when compared to hydrocarbon blowing agent materials.

Regulatory


Honeywell Solstice LBA is:

- Listed under the EPA's SNAP program
- Listed on the TSCA inventory
- VOC-exempt

% Energy Efficiency Improvement (refrigerator power consumption¹)



Honeywell Solstice LBA has a GWP of 1



For More Information

call 1.800.631.8138

or visit: www.honeywell-blowingagents.com.

Honeywell Advanced Materials

115 Tabor Road

Morris Plains, NJ 07950



RESPONSIBLE CARE
OUR COMMITMENT TO SUSTAINABILITY

Feb 2017

© 2017 Honeywell International Inc. All rights reserved.

Honeywell

Although Honeywell International Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of Honeywell International Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.